

Certification of Facsimile Transmission

I hereby certify that this paper is being facsimile transmitted
to the Patent and Trademark Office on the date shown below

Type or print name of person signing certification

Signature Martin Novack Date April 4, 2003Fax to USPTO
Group 1762703-872-9310
(3 sheets)

SJE-01720

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant(s): Paul Maurice Burling

Serial No. : 09/700,240

Group : 1762

Filed : December 12, 2000 Examiner: Blanton, Rebecca

For : HEAT RESISTANT PRODUCT AND METHOD

SUPPLEMENTAL AMENDMENT

Assistant Commissioner for Patents

Washington, DC 20231

Sir:

Please enter the following supplemental amendment.

IN THE SPECIFICATION:

Page 2, third paragraph is amended as follows:

Q1
We have also found that the resultant product has good mechanical strength properties and for example with densities in the range 250-300Kg/m³, flexural strengths of 0.15-0.45 MPa are achieved. Experiments have shown that the density is preferably no less than 140Kg/m³ to achieve acceptable flexural strength in a self-supporting product. Furthermore, the greater the proportion of the vermiculite, the more light weight the product.

FAX RECEIVED
APR 07 2003
GROUP 1700